



Karta techniczna produktu

Chemmot Ewa Kumorek spółka komandytowa
PL 32-050 Skawina, ul. Józefa Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Trade name	
PLASTI SKIN by DECO COLOR® aerosol line	
Article No	
17 000; 17 100; 17 200; 17 300; 17 400; 17 500; 17 600; 17 700; 17 800; 17 900	
Seller/Manufacturer	
Chemmot Ewa Kumorek spółka komandytowa; Józefa Piłsudskiego 59, 32-050 Skawina, Polska	
Product's description	
Flexible, fast drying mat film for any type of surface. Wide application: industry, decoration, moto tuning, home and garden. Protects against corrosion. The most important asset – easy to peel off. Paint. Don't you like it- peel it easily off!	
Main features	
Easy way to remove applied film, immediately after drying, as well No need to use cleaners or solvents – just peel it off Doesn't change the structure of painted surface Anti-slip properties Very good adhesion Resistant to high and low temperatures from -35°C to +90°C Water and weather resistant For indoor and outdoor use CFC free	
Physical and Chemical Properties	
Capacity	400 ml
Base/resin	polymer resin
Colour	clear, yellow, orange, red, blue, green, black, white, gold silver
Gloss	mat
Application temperature	15-25°C
Dust free	5-8 min
Touch free	15-20min
Hardened	16-20 h
Cover capacity	1,5-2 m ² depending on colour and type of surface by one application
High temperature resistance	from -35°C up to +90°C
VOC content	about 80%
Solids content	about 20%
Petrol resistance	none
Alcohol resistance	none
Primer usage	not recommended
Other coating applying	not recommended



Karta techniczna produktu

Chemmot Ewa Kumorek spółka komandytowa
PL 32-050 Skawina, ul. Józefa Piłsudskiego 59

Telefon: 12 276 75 45
Telefax: 12 276 78 20

DECO COLOR® znak towarowy CHEMMOT®
DECO COLOR® najlepiej postrzegany brand farb i lakierów w aerozolu

Usage

Before application read carefully instructions on the container and use according to the manufacturer's recommendations.

Recommended substrate conditions

Proper surface preparation has huge influence to final result. Fundamental principle, which relate to all surfaces prepared to painting is to grind, degrease and let it dry.

Notice: Thickness and flexibility depends on number of layers you applied. One layer is 30-40 microns. Recommended is to apply 100-120 microns, what means 3 layers at least, at 10 minutes intervals between each.

Easy way to remove applied film, immediately after drying, as well as after longer time of usage. No need to use cleaners or solvents – just peel it off.

Method of use

Apply product at temperature about 15-25°C (optimum temperature for good varnish drying).

Drying time depends also on air humidity and product density.

Painting should be made in well ventilated room.

Prior to commencing painting, shake the container for about one minute, what helps mix the varnish by the ball inside.

Perform the test spray.

Apply the varnish with few thin layers rather than one thick layer, from the distance of 25-30 centimetres.

Wait few minutes between each layer when applying.

When finished, clean the nozzle.

Put the container upside down, pressing the nozzle for the period of three seconds.

Technical Data Sheet version 05 from 01/03/2022